



## Flake Capping Compound to ASTM C617 22Kg

Code: 34-6100

Product Group: Sulphur Compound Method, Flake  
Capping Compound

Supplied in 22 kg box.

### Standards

ASTM C617, AASHTO T231

### Specification

|                       |  |
|-----------------------|--|
| Density               | 13.7 lbs./cu. ft. (2,186 kg/cu. m.).                                   |
| Tensile Strength      | 605 psi (4.2 x 10 <sup>5</sup> kg/sq m.)<br>after 48 hrs.              |
| Compressive Strength  | 5,000 psi (3.6 x 10 <sup>6</sup> kg/sq m.)<br>minimum, after<br>2 hrs. |
| Melting Range         | 23 °-24 °F (11 °-115 °C).  |
| Optimum Pouring Range | 260°-290°F (126°-143 °C).  |
| Weight                | Net 50 lbs. (22.7 kg); Shpg. 52<br>lbs. (23.6 kg).                     |

### Accessories



#### 6" Retaining Caps

Code: 34-6134

### Alternatives



#### 6" Retaining Caps

Code: 34-6134